Docket No. 134778-1

RECEIVED
CENTRAL FAX CENTER
DEC 13 2006

AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A thermoplastic composition, comprising:

about 100 parts by weight of a polycarbonate, an aromatic polycarbonate, a (co)polyestercarbonate, an aromatic (co)polyestercarbonate, or combinations thereof ~~blends thereof, or a combination comprising at least one of the foregoing polymers~~;

about 0.1 to about 10 parts by weight of an antistatic agent; and

about 0.1 to about 10 parts by weight of a polysiloxane-polyether copolymer.

2. (Original) The composition of claim 1, wherein the antistatic agent is a sulfonic acid salt according to the formula



wherein Q is nitrogen or phosphorus; R^1 is C_1-C_{40} alkyl, C_1-C_{40} haloalkyl, C_6-C_{40} aryl, (C_6-C_{12} aryl)C_1-C_{40} alkyl, or (C_1-C_{40} alkyl)C_6-C_{12} aryl; and R^2, R^3, R^4 and R^5 are each independently hydrogen, C_1-C_{20} alkyl, C_6-C_{12} aryl, (C_6-C_{12} aryl)C_1-C_{20} alkyl, or (C_1-C_{20} alkyl)C_6-C_{12} aryl.

3. (Original) The composition of claim 2, wherein Q is phosphorus and R^1 is a C_1-C_{40} haloalkyl group wherein the halo is fluoro.

4. (Original) The composition of claim 1, wherein the antistatic agent is a sulfonic acid salt according to the formula



wherein Q is nitrogen or phosporus, X is independently selected from halogen or hydrogen provided that at least one X is halogen; n, m and p are integers from 0 to 12; Y is a single bond or nitrogen, oxygen, sulfur, selenium, phosphorus, or arsenic; R^6, R^7, and R^8 are each independently C_1-C_8 alkyl or C_6-C_{12} aryl; and R^9 is C_1-C_{18} alkyl.

5. (Original) The composition of claim 4, wherein Q is phosphorus.

6. (Original) The composition of claim 1, wherein the polysiloxane-polyether copolymer comprises the structure:



wherein n is about 3 to about 5000; R^9, R^{10}, R^{11}, R^{12}, R^{13}, R^{14} are each independently hydrogen, C_1-C_{20} alkyl, C_6-C_{12} aryl, (C_1-C_{20} alkyl)C_6-C_{12} aryl, (C_6-C_{12} aryl)C_1-C_{20} alkyl, C_1-C_{20} alkoxy, or polyether group, wherein at least one of R^9, R^{10}, R^{11}, R^{12}, R^{13}, or R^{14} is a polyether group.

7. (Original) The composition of claim 6, wherein R^9, R^{14}, or both are polyethers.

8. (Original) The composition of claim 6, wherein R^{10}, R^{11}, R^{12}, R^{13} or a combination of the foregoing are polyethers.

9. (Original) The composition of claim 1, wherein the polysiloxane-polyether copolymer is



wherein x, and z independently range from 0 to about 50; y is 1 to about 50; R^{15}, R^{16}, R^{17}, R^{18}, R^{19}, R^{20}, R^{21}, R^{22}, R^{23}, R^{24}, R^{25}, and R^{26} are each independently hydrogen, C_1-C_{20} alkyl, C_6-C_{12} aryl, (C_1-C_{20} alkyl)C_6-C_{12} aryl, (C_6-C_{12} aryl)C_1-C_{20} alkyl, C_1-C_{20} alkoxy, or polyether group wherein at least one of R^{15}, R^{16}, R^{17}, R^{18}, R^{19}, R^{20}, R^{21}, R^{22}, R^{23}, R^{24}, R^{25}, and R^{26} is a polyether group.

10. (Original) The composition of claim 1, further comprising a sulfonate alkali metal salt.

11. (Currently Amended) A method for making a permanently antistatic article, comprising:

melt mixing about 100 parts by weight of a polycarbonate, an aromatic polycarbonate, a (co)polyestercarbonate, an aromatic (co)polyestercarbonate, or combinations thereof ~~blends thereof, or a combination comprising at least one of the foregoing polymers~~, about 0.1 to about 10 parts by weight of an antistatic agent, and about 0.1 to about 10 parts by weight of a polysiloxane-polyether copolymer to form a blend; and

molding the blend to form an article.

12. (Currently Amended) A sheet or film of a thermoplastic resin composition, comprising:

about 100 parts by weight of a polycarbonate, an aromatic polycarbonate, a (co)polyestercarbonate, an aromatic (co)polyestercarbonate, or combinations thereof ~~blends thereof, or a combination comprising at least one of the foregoing polymers~~;

about 0.1 to about 10 parts by weight of an sulfonic acid salt antistatic agent; and

about 0.1 to about 10 parts by weight of a polysiloxane-polyether copolymer.

13. (Original) An article prepared by the sheet or film of claim 12.

14. (Original) An article prepared from the composition of claim 1.